

DESCRIPTION

Johnstone's Trade Flortred is a highly durable one pack floor coating with excellent levels of film hardness. It is resistant to mild chemicals, water, oil, grease and impact in areas subject to light and medium levels of traffic such as walkways, and will withstand low levels of vehicle traffic. To further boost the slip resistance of Johnstone's Trade Flortred, use with Johnstone's Trade Anti-Slip Additive. Suitable for exterior use to highlight walkways, car park spaces and other markings. Not suitable for use on large external areas.

RECOMMENDED USES



For light to medium traffic areas.

SPECIAL PROPERTIES

Resistant to mild chemicals, water, oil and grease spillage.

COLOUR RANGE

Black; Clear; Dark Green (14C39); Dark Grey (18B25); Morning Mist (10A03); Princess Grey (00A05); Sherwood Green; Safety Yellow (08E51); Safety Red (04E53); Safety Blue (18E53); Tile Red; White; Tintable.

FINISH

Semi-gloss.

VOLUME S

49%

COVERAGE



Johnstone's Trade Flortred will cover up to 16 square metres per litre depending on the nature and porosity of the surface being painted.

FILM THICKNESS

Wet: 90µm, dry: 44µm.

DRYING TIME



Recoat after 16-24 hours under normal conditions. The coating is fully cured in 7 days.

TRANSPORTATION & STORAGE

To avoid risk of spillage, always store and transport in a secure upright position. **STORE AWAY FROM HEAT AND FLAME.**

THINNER

Thinner: White Spirit.

VOC CONTENT

EU limit value for this product (Cat A/i): 500 g/l (2010) This product contains max 500 g/l VOC



*Always follow the 3 step system unless you have received a Johnstone's Trade technical specification that recommends an alternative.

KEY PROPERTIES

- Improved levels of hardness and durability
- For use on concrete, steel and wooden floors
- Resistant to mild chemicals
- Semi-gloss finish

PREPARATION

All surfaces to be painted should be clean, dry and free from dust, laitance, loose and flaking material. New concrete or cement should be allowed to mature for several months before painting. Very dense smooth concrete surfaces (such as power floated concrete) normally require to be acid etched before painting in order to promote satisfactory adhesion. For more information and free Johnstone's Trade datasheets call 01924 354354 or visit www.johnstonestrade.com.

APPLICATION



Ensure maximum ventilation during application and drying. When applying to large interior surfaces or in confined spaces, wear a suitable cartridge respirator or air-fed respiratory protective equipment. Stir well before use. Apply by brush or roller which should be fully loaded for best results. Apply paint evenly and avoid overspreading. To ease application, the first coat may be thinned with up to 5% by volume of White Spirit. Allow to dry overnight before applying a second coat, if required. If more than one can of a colour is to be used in the same area, intermix before use.

CLEANING



Remove as much product as possible from application equipment before cleaning. Replace lid firmly. Clean equipment immediately after use with White Spirit or Turpentine substitute. Some local authorities have special facilities for the disposal of waste coatings. Do not empty product into drains or watercourses.

PRECAUTIONS

- Keep out of reach of children
- Avoid contact with skin and eyes
- Do not ingest
- If medical advice is needed have container or label to hand
- Please refer to Product Label & Safety Data Sheet (SDS) for hazard warnings and information on safe handling/use/transport/storage/disposal/emergency
- SDS available : www.johnstonestrade.com or call 01924 354354

SIZE

Size: 2.5 Litre and 5 Litre. Note, some colours are only available in 5 Litre.