

RUST-OLEUM[®]
INDUSTRIAL



9200 RUST-O-THANE[®]

Hardwearing, washable satin gloss polyurethane

- Automotive level UV stability; does not yellow
- Water-based formula with low odour
- High abrasion resistance, extremely scratch resistant
- Smooth satin finish with excellent flow
- Can be used on floors, walls, stairs, wood and metal

KNOW-HOW TO PROTECT[™]

WWW.RUST-OLEUM.EU

9200 RUST-O-THANE®

DESCRIPTION

Water-based satin gloss 2K polyurethane for a very durable and colourfast finish on metal or floors. Also ideal for doors, stairs, furniture, and as a topcoat for epoxy and acrylic systems.

RECOMMENDED USE

RUST-O-THANE 9200 is intended for application on interior and exterior substrates which are coated with RUST-OLEUM epoxy or acrylic coatings (e.g. RUST-OLEUM: 9100 and 5401, Pegasol or Pegalink). The application area consists of coated floors, coated walls and primed metal. Also ideal for use on stairs, doors, kitchen walls, floors and more.

RUST-O-THANE 9200 assures appropriate protection against solvents, moderate alkalines, weak acids and chemical cleaning. Especially recommended where general urethane performance like excellent weather resistance (UV), easy cleaning and abrasion resistance is required.

TECHNICAL DATA

Density (g/cm ³):	1,23
Gloss Level:	Satin
Solids content in volume:	37%
Heat Resistance:	90°C (dry heat), above 65°C discoloration may occur
Mixing Ratio:	Base : Activator = 5.66 : 1 by volume

DRY TIMES BY 20° C/RV 50%

Touch dry:	2 hours
Dry to handle:	4 hours
Dry to recoat:	24 hours
Fully cured:	2 days
Pot Life:	2 hours for a 5 litre mix at 20°C
Induction Time:	5 minutes

RECOMMENDED WET FILM THICKNESS

110 µm

RECOMMENDED DRY FILM THICKNESS

40 µm

THEORETICAL CONSUMPTION

6,2 m²/l at 60 µm dry (depending on colour) for floors.

9,2 m²/l at 40 µm dry (depending on colour) for other applications.

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Remove grease, oil and all other surface contamination using alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Sand previous coatings that are in good condition to remove gloss and to roughen the surface slightly. Assure that the previous coating is compatible with the RUST-O-THANE 9200 by making a test application. Remove bad adhering coatings by scraping, wire brushing or sanding. (Spot)prime with commended Rust-Oleum or Mathys coatings. The surface must be clean and dry during application.

DIRECTIONS FOR USE

Add activator gradually to base material and mix with a mechanical mixing device. Do not dilute during the pot-life. Do not use after 2 hours. Do not store residue of mixed product in a closed can.

APPLICATION CONDITIONS

Temperature of air, substrate and coating material between 5°C and 35°C and relative humidity below 80 %. The substrate temperature must be at least 3°C above dew point.

APPLICATION & THINNING: BRUSH

Use undiluted. Use natural bristles, long hair brushes.

APPLICATION & THINNING: ROLLER

Use undiluted. Use medium nap (polyamide, 8-12 mm). Apply slowly in even strokes.

APPLICATION & THINNING: AIRLESS SPRAY

Use undiluted. Pneumatic and electric airless equipment. Tip size: 0.013-0.015 inch. Fluid pressure: 200 bar.

CLEANING OF EQUIPMENT / SPILLS

Water and soap, before drying

REMARKS

Max dry film thickness for floors: 75 µm dry, equals 200 µm wet. For walls: 60 µm dry, equals 160 µm wet.

For use on floors submitted to heavy abrasion, standard and medium colours are recommended. In case of deep and/or bright tones (red, yellow, orange, green, blue etc), it is advised to apply a clear topcoat.

The product is not recommended in case of stagnating water and/or immersion.

SAFETY DATA

VOC level:	35 g/l
VOC readymix:	35 g/l
VOC category:	A/j
VOC limit:	140 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

Base Minimum of 2 years and activator Minimum of 1 year from the date of production in unopened cans, if stored in dry, well-ventilated and frost-free areas, not in direct sunlight at temperatures between 5° and 35° C. Opened activator cans must be used within 1 week.

Date issued: 24/06/2022

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu