



## HARDENER FOR OIL STAIN

Shortens drying times for Oil Stain significantly.



6631  
Clear



### PRODUCT DESCRIPTION

Special clear polyisocyanate hardening additive for Osmo Oil Stain to reduce drying times.

### RECOMMENDED USE

Osmo Hardener for Oil Stain acts as an additive for Osmo Oil Stain that accelerates the drying process.

### INGREDIENTS

Aliphatic polyisocyanate, methoxy propyl acetate.  
Detailed declaration of ingredients available upon request.

### TECHNICAL DATA

Specific weight: 1.15 g/cm<sup>3</sup>  
Viscosity: 36s (4 mm, DIN 53211)  
Odour: faint/mild, odourless after drying  
Flash point: >45 °C acc. DIN 53213

### STORAGE

Up to 1 year and longer if can is kept dry and closed tightly. Leftover product mixture cannot be stored and reused.

### SURFACE PREPARATION

Preparations before use of Osmo Oil Stain are not influenced by the application of the hardener additive. These are valid without any restrictions. For this purpose, please observe the product information for Osmo Oil Stain. The finished surface is influenced by several factors, including the condition of the wood. Therefore, a trial application is always required, especially for unfamiliar surfaces.

### METHODS OF APPLICATION

Add Osmo Hardener for Oil Stain completely to the can of Oil Stain (1.0 litre) and stir so that both components are mixed well. Further processing to be carried out corresponds to that of Oil Stain.

Note: Pot time is reduced down to 60 minutes by adding the Hardener. Please do not mix together more material than you can process with certainty within 45 minutes. If you do not use the entire can of Oil Stain, add 6% Hardener – mix in a separate container!

### CLEANING OF TOOLS

With Osmo Brush Cleaner (free of aromatic compounds).

### Drying time

Approx. 3-4 hours (normal climatic conditions, 23 °C/ 50 % rel. humidity). Lower temperatures and/or higher air humidity can increase the drying time. Ventilate well while drying.

### COVERAGE

The product coverage of Oil Stain is not changed by adding hardener.

### NOTE

Pot time is reduced down to 60 minutes by adding the Hardener. Please do not mix together more material than you can process with certainty within 45 minutes.

### CAUTION

Flammable liquid and vapour. Harmful if inhaled. Contains isocyanates. May produce an allergic reaction. May cause respiratory irritation.



## CAUTION

Keep out of reach of children. Read label before use. Keep away from heat/ open flames. No smoking. Do not breathe mist/vapours/spray. Wear protective gloves. If medical advice is needed, have product container or label at hand. Use only outdoors or in a well-ventilated area. IF ON SKIN: Wash with plenty of water and soap. IF INHALED: Remove person to fresh air and keep comfortable for breathing. Dispose of contents/container in accordance with chemical waste disposal regulations.

Product contains: Hexamethylene 1,6-diisocyanato homopolymer.

## Warning



## DISPOSAL

Dispose of leftover product and completely emptied packaging according to local official guidelines (waste code number 08 05 01). Only completely emptied cans can be recycled.

## COLOUR TONE

6631 Clear

## Size

0.06 L

The above mentioned information is provided to the best of our knowledge however without any liability.

Version 02/17